



PC-ABSCOM™ B100A

Polycarbonate + Acrylonitrile Butadiene Styrene

PC-ABSCOM B100A is a PC/ABS alloy with superior heat distortion and impact properties. Typical applications include mobile phone housing and chrome-plated applications.

Typical Property	Typical Value	Unit	Test Method based on
Melt Flow (260°C / 5 kg)	18	g/10 min	ISO 1133
Izod Notched Impact RT	40	kJ/m ²	ISO 180/1A
Tensile Strength at Yield	49	MPa	ISO 527
Elongation at Yield	3.7	%	ISO 527
Vicat Softening point (B/50)	108	°C	ISO 306
Density	1100	Kg/m ³	ISO 1183
Other characteristics:	Suitable for electroplating		

All data given are typical product data and do not represent minimum values.

The actual value may vary depending on colour and additives.

All information supplied by or on behalf of PCL in relation to its products whether in the nature of data, recommendations or otherwise is supported by research and believed reliable but PCL assumes no liability whatsoever in respect of application, processing or use of afore-mentioned products, or any consequences thereof. No liability whatsoever shall attach to PCL for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or other use of the afore-mentioned information or products by the user.

The user undertakes all liability in respect of the application, processing or use of the afore mentioned information or product, whose properties he shall verify or any consequence thereof.

Edwardson Road, Meadowfield Industrial Estate, Durham, DH7 8RL, UK

tel: +44 (0)191 378 37 37



fax: +44 (0)191 378 17 17

www.polymer-compounders.com

