

NOTOXICOM S6000

Acrylonitrile Styrene Acrylate/Polycarbonate/Polyphosphonate-cocarbonate

NOTOXICOM S6000 is a UL94 Halogen Free 1.6/0.8 mm V0 Flame Retardant rated PC/ASA with superior heat, toxicity and density performance.

Physical Properties	Typical Value	Unit	Test Method based on
Density	1150	Kg/m ³	ISO 1183
Water absorption (23°C, sat)	0.70	%	ISO 62
Moisture absorption (23°C, 50% RH)	0.22	%	ISO 62
Mould shrinkage	0.4-0.7	%	ISO 294
Melt Flow (260°C / 5 kg)	18	g/10 min	ISO 1133
Glow Wire Flammability 3mm	960	Deg C	IEC 60695-2-11
Flammability (1.5mm)	V0		UL94*
Flammability (0.8 mm)	V0		UL94*

All data given are typical product data and do not represent minimum values.

The actual value may vary depending on colour and additives. * - Tested externally by Intertek.

All information supplied by or on behalf of PCL in relation to its products whether in the nature of data, recommendations or otherwise is supported by research and believed reliable, but PCL assumes no liability whatsoever in respect of application, processing or use of afore-mentioned products, or any consequences thereof. No liability whatsoever shall attach to PCL for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or other use of the afore-mentioned information or products by the user.

The user undertakes all liability in respect of the application, processing or use of the afore mentioned information or product, whose properties he shall verify or any consequence thereof.


Edwardson Road, Meadowfield Industrial Estate, Meadowfield, Durham, DH7 8RL, UK

tel: +44 (0)191 378 37 37



fax: +44 (0)191 378 17 17

www.polymer-compounders.com



POLYMER COMPOUNDERS LIMITED

NOTOXICOM

S6000

Mechanical Properties	Typical Value	Unit	Test Method based on
Tensile Strength at Yield (50mm/min)	57	MPa	ISO 527
Tensile Elongation at Break (50mm/min)	70	%	ISO 527
Tensile Modulus (1mm/min)	2500	MPa	ISO 527
Flexural Strength	85	MPa	ISO 178
Izod Notched Impact (RT)	16	kJ/m ²	ISO 180/1A
Charpy Notched Impact (RT)	16	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact (RT)	NB	kJ/m ²	ISO 179/1eU
Rockwell hardness	120	R	ISO 2039-2

All data given are typical product data and do not represent minimum values.

The actual value may vary depending on colour and additives. * - Tested externally by Intertek.

All information supplied by or on behalf of PCL in relation to its products whether in the nature of data, recommendations or otherwise is supported by research and believed reliable, but PCL assumes no liability whatsoever in respect of application, processing or use of afore-mentioned products, or any consequences thereof. No liability whatsoever shall attach to PCL for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or other use of the afore-mentioned information or products by the user.

The user undertakes all liability in respect of the application, processing or use of the afore mentioned information or product, whose properties he shall verify or any consequence thereof.


Edwards Road, Meadowfield Industrial Estate, Meadowfield, Durham, DH7 8RL, UK

tel: +44 (0)191 378 37 37



fax: +44 (0)191 378 17 17

www.polymer-compounders.com



POLYMER COMPOUNDERS LIMITED

NOTOXICOM

S6000

Thermal Properties	Typical Value	Unit	Test Method based on
CTE linear	8.0E-05	1/°C	ISO 11359-2 (Parallel)
HDT (0.46 MPa)	130	°C	ISO 75/Ae
HDT (1.8 MPa)	107	°C	ISO 75/Ae
Vicat Softening point (B/50)	125	°C	ISO 306

Processing Properties	Typical Value	Unit
Melt Temperature	250-260	°C
Mould Temperature	70	°C
Injection Velocity	60.0	mm/s
Drying Time	2 to 4	hr
Drying Temperature	90	°C

All data given are typical product data and do not represent minimum values.

The actual value may vary depending on colour and additives. * - Tested externally by Intertek.

All information supplied by or on behalf of PCL in relation to its products whether in the nature of data, recommendations or otherwise is supported by research and believed reliable, but PCL assumes no liability whatsoever in respect of application, processing or use of afore-mentioned products, or any consequences thereof. No liability whatsoever shall attach to PCL for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or other use of the afore-mentioned information or products by the user.

The user undertakes all liability in respect of the application, processing or use of the afore mentioned information or product, whose properties he shall verify or any consequence thereof.

Edwardson Road, Meadowfield Industrial Estate, Meadowfield, Durham, DH7 8RL, UK

tel: +44 (0)191 378 37 37



fax: +44 (0)191 378 17 17

www.polymer-compounders.com